DECORK

Cork based decorative finish applicable on walls, floors and facades.

Decorative finish made of cork and water based resins (grain size 0 - 1 mm; 0 - 0.04 in) for the decoration of floors, walls, ceilings and facades, for indoor and outdoor. The coating has all the benefits of cork: breathability, thermal insulation, an excellent fire reaction, weathering resistance and durability. It is possible to create endless aesthetical effects, which can have different textures.

BENEFITS

- Suitable to create decorative effects.
- Suitable for indoor and outdoor.
- Breathable and water-repellent.
- · Elastic.
- Excellent aesthetic effect.
- Easy and quick application.
- LEED accredited and CE branded.

YIELD


 $0.8 - 1.0 \text{ kg/m}^2 \text{ in } 2 \text{ coats.}$ $0.16 - 0.2 \text{ lb/ft}^2 \text{ in } 2 \text{ coats.}$

COLOR

Diasen color chart.

APPLICATION FIELDS

Product designed for the coating and the decoration of internal walls, ceilings, floors and external facades. *Decork* shows excellent adhesion abilities on any kind of support and for this reason, with the correct primer, it can be used on different substrates: metal, plaster, cement supports and tiles. *Decork* is suitable both indoor and outdoor.



PACKAGING

18 kg (39.6 lb) plastic bucket + 2 kg (4.4 lb) of color. Pallet: 32 bucket (576 kg - 1267.2 lb) + 32 packaging of color (64 kg - 140.8 lb).

UB1 Color

18 kg (39.6 lb) plastic bucket + 4.5 kg (9.9 lb) of color. Pallet: 32 bucket (576 kg - 1267.2 lb) + 32 packaging of color (144 kg - 316.8 lb).

STORAGE

Store the product in its original containers perfectly closed, in well ventilated areas, away from sunlight, water and frost, at temperatures between +5°C and +35°C (41°F and 95°F). Storage time: 12 months.


PREPARATION OF SUPPORT

The support must be completely hardened and resistant enough. The surface must be perfectly levelled, thoroughly clean, dry, well consolidated, without oils, greases debris or detaching parts or other materials that may compromise the product adhesion.

If the surface is crumbly in its entirety, totally scrape it until obtaining a good support and restore lesions or damaged parts with suitable mortar.







Decorative

Whereas all indications and recommendations supplied herein are stated to the best of our experience and knowledge, they should be considered as indicative only and should be confirmed by exhaustive practical applications. Diasen doesn't know the peculiarity of the processing, or the characteristics of the support. Therefore the applicator should carry out preliminary tests, to verify the suitability to the foreseen application, and in any case he will take the responsibility of the intended use. In case of uncertainties or doubts, please contact the company's technical department, provided that this is only a simple assistance for the applicator: he should have the appropriate capabilities and experience to determine the more suitable solution. Always respect the latest update of the technical sheet available on <u>www.diasen.com</u>.



Technical Data							
Features		Unit					
Yield	0.8 - 1.0 in two coats 0.16 - 0.2 in two coats	kg/m ² lb/ft ²					
Aspect	paste	-					
Colour	Diasen color chart	-					
Dilution	If necessary max 5% By trowel (0.9 I – 0.2 gal per 18 kg – 39.6 lb bag) If necessary max 10% By spray (1.8 I – 0.47 gal per 18 kg – 39.6 lb bag)	-					
Waiting time between 1 st and 2 nd coat (T=23°C/73.4°F; R.H. 50%)	about 8 - 10	hours					
Grain size	0 - 1 0 - 0.04	mm in					
Application temperature	+5 /+35 +41/+95	°C °F					
Drying time (T=23°C/73.4°F; R.H. 50%))	10	hours					
Storage	12 months in original containers and well ventilated months areas						
	18 kg (39.6 lb) plastic bucket + 2 kg (4.4 lb) of color						
Packaging	UB1 Color: 18 kg (39.6 lb) plastic bucket + 4.5 kg (9.9 lb) of color.	kg					

LEED [®] Credits						
Standard GBC HOME						
Thematic area	Credit	Points				
Energy & Atmosphere	EAp1 - Minimum Energy Performance	mandatory				
	EAp2 – Minimum Performance of matt package	mandatory				
	EAc1 - Optimize Energy Performance	From 1 to 27				
	EAc2 – Advanced performance of matt package	2				
Materials & Resources	MRp2 – Construction Waste Management	mandatory				
	MRc2 - Construction Waste Management	From 1 to 2				
	MRc3 – Low Emitting Materials	From 1 to 3				
	MRc4 – Recycled Content	From 1 to 2				
	MRc5 – Regional Materials	From 1 to 2				
	MRc6 – Rapidly Renewable Materials	2				

Decorative

Whereas all indications and recommendations supplied herein are stated to the best of our experience and knowledge, they should be considered as indicative only and should be confirmed by exhaustive practical applications. Diasen doesn't know the peculiarity of the processing, or the characteristics of the support. Therefore the applicator should carry out preliminary tests, to verify the suitability to the foreseen application, and in any case he will take the responsibility of the intended use. In case of uncertainties or doubts, please contact the company's technical department, provided that this is only a simple assistance for the applicator. Always respect the latest update of the technical sheet available on <u>www.diasen.com</u>.



2/6

Standard LEED for New Construction & Major Renovation, LEED for Schools, LEED for Core & Shell, v. 2009						
Thematic area	Credit	Points				
Energy & Atmosphere	EAp2 - Minimum Energy Performance	Mandatory				
	EAc1 – Optimize Energy Performance	From 1 to 19				
Materials & Resources	MRc2- Construction Waste Management	From 1 to 2				
	MRc4 – Recycled Content	From 1 to 2				
	MRc5 – Regional Materials	From 1 to 2				
	MRc6 - Rapidly Renewable Materials	1				
Indoor Environmental Quality	IEQc3.2 - Construction Indoor Air Quality Management Plan—Before Occupancy	1				
	IEQc4.2 - Low Emitting Materials - Paints and Coatings	1				

Final performances		Unit	Regulation	Results
Elasticity	60%	-	ISO 527-1	-
Crack Bridging Ability	2.5 0.099	Mm in	-	-
Weathering Test	1680 hours (10 year*)	hours/ years	EN ISO 11507	-
Thermal conductivity (λ)	0.086	W/mK	EN 12667	-
Water vapour permeability	μ = 15	-	EN ISO 7783	-
Abrasion resistance of the system Decork + Aquafloor Eco (shiny version) Taber Wear Index	70	-	ASTM D 4060	-
Abrasion resistance of the system Decork + Aquafloor Eco (matt version) Taber Wear Index	55	-	ASTM D 4060	-

* 1680 hours of weathering test are equal to about 10 years. This equivalence is merely indicative and it may vary depending on the weather conditions of the place where the product will be used.
The above data, even if carried out according to regulated tests are indicative and they may change when specific building site conditions vary.

Decorative

Whereas all indications and recommendations supplied herein are stated to the best of our experience and knowledge, they should be considered as indicative only and should be confirmed by exhaustive practical applications. Diasen doesn't know the peculiarity of the processing, or the characteristics of the support. Therefore the applicator should carry out preliminary tests, to verify the suitability to the foreseen application, and in any case he will take the responsibility of the intended use. In case of uncertainties or doubts, please contact the company's technical department, provided that this is only a simple assistance for the applicator: he should have the appropriate capabilities and experience to determine the more suitable solution. Always respect the latest update of the technical sheet available on www.diasen.com.



In case of hydro-cleaning, wait for the complete drying of the support.

Potential humidity in the support or the vapour due to radiation may compromise the adhesion of the applied product.

On horizontal flat surfaces consider suitable scope to allow the water down flow.

Decork adheres to different kind of support without the primer, it is anyway recommended to perform a test to verify the adhesion or the need to use a primer.

Diathonite plasters or new plasters

Make sure that the plaster is well levelled so it is as smooth as possible. Otherwise, apply a layer of a suitable Diasen's smoother (see technical data sheet). Both on plaster and directly on plaster apply the specific fixative *D20* (see technical data sheet). In case of weaked surface and with micro cracks, apply the white foundation *Color Primer* (see technical

Old plaster

data sheet).

Make sure that the plaster is compact and well bonded to the support, otherwise partially or totally remove it and re-make it.

In case of painted plasters, according to the wide range of paints on the market, it is recommended to perform an adhesion test to verify the suitability for the application or the need to use the primer *D20* and/or *Color Primer* (see technical data sheet).

On rough plasters, *Decork*, can directly be applied. In case of dusty supports, use the fixative *D20* (see technical data sheet).

Plasterboard

On plasterboard surfaces, make sure that the joints are sealed and smoothed. Apply the fixative *D20* (see technical data sheet).

Concrete

In case of new realised cement substrate, this must be sufficiently cured.

In presence of lesions, holes or irregular areas, restore them with suitable cement mortar.

For a better adhesion on smooth and not moist concrete, it is recommended to smooth it, clean it and then apply *Grip Primer* (see technical data sheet).

For the treatment of iron bars, apply the *Anticorrosive 2K* (see technical data sheet).

To obtain a better adhesion on smooth and not absorbent concrete, it is recommended the use of *Grip Primer* (see technical data sheet).

On moist supports, in order to avoid blistering or detachment phenomena, use *Vapostop* (see technical data sheet).

If the support is affected by rising damp, it is necessary the use of *WATstop* (see technical data sheet). *WATstop* can also be used to fill small cracks and to level the support.

On rough concrete use the primer Vapostop.

Tiled floors

Make sure that the tiles are well bonded to the support, otherwise remove them and restore them with suitable cement mortar.

The tiled surface must not present traces of detaching substances as greases, oils, chemical products etc.

Carefully clean the support and treat the surface with *Grip Primer* (see technical data sheet).

To fill tiles joints and to create a perfectly levelled surface, use *Vaposhield* (see technical data sheet) applied by hand with steel or rubberized trowel in two coats. *Vaposhield* must be used even if the support is moist or affected by rising damp.

According to the wide range of tiles on the market, it is recommended to perform a test to verify the correct adhesion of the system.

Wood

Thoroughly clean the surface by removing dust, debris and detaching parts. The wood must be completely dry, well resistant and stable.

Treat the wooden surfaces with the primer *Grip Primer* (see technical data sheet) before the application of *Decork*.

Do not apply the product on wooden supports, matchboarding or on supports with many joints.

Metal

Thoroughly clean the surface by removing all dirt and potential varnishes not well attached.

Before the application of *Decork*, apply *Grip Primer* (see technical data sheet) on the surface.

In presence of rust, before the application of *Grip Primer*, treat the surface with *Rust Converter* (see technical data sheet).

Decorative

Whereas all indications and recommendations supplied herein are stated to the best of our experience and knowledge, they should be considered as indicative only and should be confirmed by exhaustive practical applications. Diasen doesn't know the peculiarity of the processing, or the characteristics of the support. Therefore the applicator should carry out preliminary tests, to verify the suitability to the foreseen application, and in any case he will take the responsibility of the intended use. In case of uncertainties or doubts, please contact the company's technical department, provided that this is only a simple assistance for the applicator: he should have the appropriate capabilities and experience to determine the more suitable solution. Always respect the latest update of the technical sheet available on <u>www.diasen.com</u>.



If the metal surface is painted, it is recommended to perform a test to verify the correct adhesion of the system.

Smooth surfaces

On particularly smooth and not absorbent surfaces use the specific primer *Grip Primer* (see technical data sheet).

For supports not mentioned in technical data sheet, please contact Diasen technical department.

Treatment of joints

Potential joints on the supports (joints between panels made of concrete or of other materials, expansion, control or insulation joints) must be treated, before the application of *Decork*, with the polyurethane sealant *Diaseal Strong* (see technical data sheet).

Treat points in contact with doorsteps or windows with the sealant *Diaseal Strong*.

MIXING

Always mix the product before the application with helical drill until obtaining a homogeneous mixture.

- Completely pour the content of the bag in the bucket and add the entire colour.
- Mix the compound for at least 2 or 3 minutes, until obtaining a mixture with uniform colour.
- The product is ready to use and generally it does not need to be diluted. In extremely hot climatic conditions, it is possible to add:
 - For hand application, maximum 5% of water (0.9 I 0.2 gal of water each 18 kg 39.6 lb packaging).
- For hopper **gun application**, maximum 10% of water (1.8 I 0.47 gal per 18 kg 39.6 lb packaging).
- It is recommended to dilute the product always in the same way to avoid colour changes.

Mix again the compound.

Never add other substances to the product.

APPLICATION

Application by hand

- **1.** Wait for the complete drying of the primer possibly used.
- 2. Apply a first abundant coat of *Decork* by steel trowel with rounded edges. The first layer can be used as a smoothing layer to uniform the surface. In case of rain over not completely dry product, carefully verify the suitability of the next covering.
- **3.** When the first layer is completely dry (about 10 hours at 23°C/73.4°F and 50% relative humidity), apply a second thin of product to finish. Do not use too much product for the second coat. For a better result and a more homogeneous coating, it is recommended to cross the coats.
- **4.** Smooth as soon after the application with a 45° rounded edge plastic trowel
- Application time: about 80/110 m² 860.8/1183.6 ft² per day.

Application with hopper gun DS-Spray Gun

- **1.** Wait for the complete drying of the primer possibly used.
- 2. The hopper gun must have:
 minimum pressure of the compressor 5.0 bar;
 nozzle diameter 8.0 mm 0.31 in.
- **3.** Apply a first coat of *Decork* to cover the whole surface. In case of rain over not perfectly dry product, carefully verify the suitability of the next covering.
- **3.** When the first coat is completely dry (about 10 hours at 23°C/73.4°F and 50% relative humidity), apply a second coat of *Decork* until complete covering of the substrate. To obtain a better result and a more homogeneous coating, it is recommended to cross the coats.
- 4. Do not smooth.
- 5. Application time: about 200/250 m² 2152/2690 ft^2 per day.

Decork can also be applied by **spraying machine** DS-5500 Texture Sprayer, nozzle diameter 4.00 mm – 0.16 in, pressure level 4 (4.0 atm); in this case, the application time ranges from 700 and 800 m² – 7532 and 8608 ft² per day.

Decorative

Whereas all indications and recommendations supplied herein are stated to the best of our experience and knowledge, they should be considered as indicative only and should be confirmed by exhaustive practical applications. Diasen doesn't know the peculiarity of the processing, or the characteristics of the support. Therefore the applicator should carry out preliminary tests, to verify the suitability to the foreseen application, and in any case he will take the responsibility of the intended use. In case of uncertainties or doubts, please contact the company's technical department, provided that this is only a simple assistance for the applicator: he should have the appropriate capabilities and experience to determine the more suitable solution. Always respect the latest update of the technical sheet available on <u>www.diasen.com</u>.



At the end of the application of the second coat, to obtain a smooth surface, the finish *Decork* can be sanded and then protected with *Aquafloor Eco* (see technical data sheet).

For floor applications, the decorative finish *Decork* must always be protected with *Aquafloor Eco* (see technical data sheet).

To create decorative effects, the finish *Decork* must be applied in combination with *Decorkoat* (see technical data sheet) and must be sanded. Then protect the surface with *Aquafloor Eco* (see technical data sheet).

DRYING TIME

At a temperature of 23° C/ 73.4° F and 50° relative humidity, the product dries in about 10 hours.

- Drying time is influenced by environmental relative humidity and by temperature and may significantly change.
- Protect *Decork* during the drying from rain, frost, direct sunlight and wind for at least 2hours at a temperature of 23°C/73.4°F.
- If applied in higher amount than the expected ones, drying time may significantly increase.

SUGGESTIONS

- Do not apply at environmental temperature or at support temperature lower than +5°C (41°F) and higher than +35°C (95°F).
- During summer season apply the product in the cooler hours of the day, away from sunlight.
- Do not apply with imminent threat or frost, in conditions of strong fog or with relative humidity level higher than 70%.
- Apply the product on completely dry surfaces.
- Protect the product from pouring rain until complete drying.
- Before the product application, it is recommended to cover each element that will not be coated.
- Store the unused product in the original packaging.

CLEANING

Wash tools with water right after the use.

When the product is completely dry, for the cleaning, it is recommended to use neutral and not aggressive detergents. Choose the most suitable cleaning method (sponge, brush or high-pressure water jet machine) according to the type of dirt.

SAFETY

While handling, always use personal protective equipments and respect the instructions described in product safety data sheet.

GREEN BUILDING FUTURE



Decorative