



ADX.0167

SANATROCK SA

Additive mix in powder for macro-porous, dehumidifying plaster

Dosage

2 - 3 kg /m²/cm

Packaging

- Bag 15 kg
- Pallet 750 kg

Application

- To be added to other components
- Apply by hand
- Brick trowel
- Finishing trowel

Family
Admix

Type
Multi-purpose powder concentrates for manufacturing thixotropic and adhesive mortars

Product Lines
• **Building**
• **Opus**
• **Sanageb**

Functional Categories
• **Masonry plastering with plasters and skims**
• **Manufacturing plasters and mortars "in situ"**

Components
Single-component

Appearance
Powder

Certifications and legislations



Sanageb - Prodotti naturali per la Bioedilizia

Product belonging to Sanageb, Azichem's product line dedicated to green-building, sustainability in constructions and bio-architecture since 1994.

General description

Binder mix, additive, to add to the preset quantity of clean and selected sand, to prepare on site for macro-porous, dehumidifying, restorative plasters, in bio-architectural works and renovation of ancient and/or monumental buildings.

General features

It is a mix of a high action dehumidifier, ready to use, only mix with water with a NHL natural hydraulic lime base, Botticino, kaolin, silicate and lime aggregates, mineral fibres and specific agents. It is a mix, together with the adequate inert substances, that enables plaster to be created with high breathability, free of cement, resins or solvents and radio-emitting agents, in compliance with bio-architectural parameters

Fields of application


Breathable dehumidifying plaster on the walls (on adding aggregates).


Available colours

- Light gray


Basic features


 Max. recommended thickness:
4 cm

 Min. recommended thickness:
2 cm

 Pot-life:
60 (20 °C) min

 Shelf-life:
12 months

 Solvent-free

 Temperature of use:
5-35 °C

Technical specifications

Breathability (UNI EN 1015-19): 11 μ

Compressive strength (UNI EN 1015-11): 2-4 N/mm²

Density (UNI EN 1015-6): 1400 kg/m³

Flexural strength (UNI EN 1015-11): 1-2 N/mm²

Setting time: 4 h

Static elastic modulus (EN 13142): 3.000 - 5.000 N/mm²

Tools cleansing

- Water

Applicable on

- Bricks
- Mixed walls (bricks and stones)
- Brickworks
- Stone walls

IF YOU WANT TO SOLVE IT


www.azichem.com

Updated: 24/02/2018
General sales conditions and legal notices on
www.azichem.com/disclaimer

Substrate preparation

Prepare the surface to plaster by removing, if present, the existing plaster, up to a height over approx. 50/100 cm compared to the line of persistent damp. The walls for application should in any case be clean, intact, free of containment, dust, flaking or inconsistent parts, conveniently saturated with water (saturated to dry surfaces). In the presence of saline efflorescence, accurately remove it and give a preventive treatment with a spray application of SANAREG. Then, a subsequent preliminary construction of a rough coat with breathable grip, with the specifically prepared UNTERSANA, or "spraying" (here and there) the same mix as described below.

Instructions for use

Prepare the plaster by firstly placing in the mixer approx. 2/3 water for the necessary mix, and then respectively adding SANATROCK SA and clean, select sand with the desired granulometry (you are advised to use sand with a maximum diameter of up to 2-3 mm). For packaging in the warehouse, comply with the following use instructions:

- kg15 SANATROCK SA
- kg 35-40 sand with a max granulometry 2-3 mm.
- litres 12-13 of water (the quantity of water can decrease according to the humidity in the sand used).

During preparation of the mix, pay attention and add the useful amount of water to obtain an even and creamy mix with the weight/litre of approx 1.3 - 1.5 Kg. This objective is however very easy to reach with minimum attention to the useful mixing time.

On the wall, previously make adequate "level stops" (strips are recommended using mortar obtained or wooden boards adequately placed in position and to plumb).

Apply the product with a trowel with a total thickness of approx 2-3 cm. Do not carry out any finishing, smoothing or crushing operation with the trowel or the blade of the mortar applied. Strike the "level stops" leaving the surface rough and leave to harden as is. Skim and finish the following day, possibly with the specific SANASTOF dehumidifying coat or definitively with a skim coat with a breathability index (μ) under 11.

Normally for a building site cement mixer with 200 litres, you are advised to initially add 100 kg of SANATROCK SA, 225 kg of sand and 45 litres of water. During mixing, add water to the mix until you reach the desired consistency (based on the humidity rate of the sand used you may need more or less litres of water). The water normally necessary in the mix is around 16-18% in weight compared to the total weight of the mix (SANATROCK SA + sand). Continue to mix until you obtain an even mix free of lumps. With a 25 kg bag of SANATROCK SA you can normally plaster 3.5 m² of wall at 2 cm thick.

Apply the mix obtained using a trowel or plastering machine. Finish with skimming systems that are definitely breathable, such as SANASTOF.

Storage and preservation

Store the product in its original packing, in a fresh and dry environment, avoiding frost and direct sunlight. Inadequate storage of the product may result in a loss of rheological performance. Protect from humidity.



www.azichem.com

Updated: **24/02/2018**
General sales conditions and legal notices on www.azichem.com/disclaimer

Warnings, Precautions and Ecology

Technical and performance data outlined in this document are the result of laboratory testing conducted in a conditioned environment, as such they can result as considerably changed from operating and application conditions. The need follows to carry out preliminary tests in actual use conditions.

The user is required to check the product's most recent Material Safety Data Sheet, reporting physical-chemical and toxicological data, risk phrases and other useful information on how to safely transport, use and dispose of the product and its packaging. It is also reminded that the product and its packaging must not be dispersed in the environment for any reason.

For thicknesses over 2 cm, as well as to improve anti-cracking, you should add a plaster holding mesh (ARMAGLASS 140).

SANATROCK SA is produced/distributed by



Via Giovanni Gentile, 16/A - 46044 Goito (MN), Italy
info@azichem.com Tel. +39 0376.604185 /604365 Fax +39 0376 604398



www.azichem.com

Updated: **24/02/2018**
General sales conditions and legal
notices on
www.azichem.com/disclaimer