

SportFloor

Scheda Tecnica Revisione : del :

Product's description Hard-elastic, water based paint for tennis-courts

Sport Floor is a modified, acrylic resins based paint with internal plasticization in water medium, with dyeing pigments and filling inert particles, resistant to weather and to UV rays. Thanks to its specific composition, **Sport Floor** has got a particular abradability and washability. It does not contain dangerous substances and it does not produce unpleasant fumes; strong consolidating, dust-proof, uninflammable power. It can be over-applied even with synthetic, polyurethane, epoxy, coloured or colourless finishes.

Practical advice Suitable for cement or concrete, mineral, synthetic and bituminous mixtures. Separators for

internal car parks; tennis-courts, gymnasiums, garages, cellars, rooms requiring a protection from

dust and a higher aesthetic effect.

Technical features

Aspect		Glazed – matt
Color		White, red, green, yellow, blue
Density Kg/Lt.		1,50 <u>+</u> 0,05
Viscosity 25°c		10000 – 3000 mpa s
Solid content by volume %		62 <u>+</u> 2%
Theoretical spreading rate Sq.m/l – gr/m2		6 Sq.m./I per coat
Typical thickness humid/dry micron		100 dry – 170 humid
Mixing ratio Base/Hardener		Single-component product
Pot Life		Not applicable
Thinner		Isoacril 1:5 thinned or volume water
Painting method	Brush	1° coat 20 - 30% thinning - 2° coat 10 – 15%
		thinning
	Roller	1° and 2° coat 15% thinning
	Spray	Not suitable
	Airless Spray	Not suitable
Drying times 25°C	Untouched :	1 hour
2.,8	Dry to the touch :	6 hours
	Absolutely dry :	24 hours
Can be trampled		After 24 hours
Min./ Max. over-application times		6 hours / no limitation
Flash point		Uninflammable
Shelf life		24 months
Standard package		l. 14 – l. 5

Notes

Keep in a dry place, far from frost and direct sunlight.



SportFloor

Scheda Tecnica Revisione : del :

Application	Preparation of the surfaces
instructions	<u>Concrete or cement</u> : check that the surface has been seasoned for at least 28 days. Wash out or brush off any trace of dust and grease. Apply one coat of dust-proof, strengthening primer Murofix (solvent fixative), or Isoacril max. 1:6 water thinned. After complete drying, evenly apply by roller or by brush
	<u>Synthetic bituminous surfaces:</u> make sure that they are compact and free from peeling parts. Repair any imperfections. Apply a first coat of Sport Floor , 25 – 30% thinned, as indicated on the technical data. After at least 6 hours, apply a second coat of Sport Floor 10% thinned, as indicated on the technical data
	Application notes:
	do not apply the product, in case of rising damp, at temperatures below +5 °C and above + 40 °C, with relative humidity below 75%.
	Do not apply during rainy nor windy days.
	After application, protect the external surfaces from rain for at least 48 hours.
	Wash tools with water, after use.
	Because of the material to be treated typology and its porosity variability, it is not possible to fix a specific spreading rate, therefore it is recommended to make a previous test, to have an idea of the product real consumption.
It is recommended for	Surfaces exposed to marine, urban, country environments and to the inclemency of the weather.
It is not recommended	
for	Industrial paving topcoat, requiring a particular resistance to chemical agents or to strong mechanical stress.
Recommended primers and intermediates	Murofix, Isoacril, Emultex wp, Poliflat trasparente, Finilac lucido, Finilac no slip.



SportFloor

Scheda Tecnica Revisione : del :

Safety precautions Uninflammable product. No labelling required, according to the standards in force.

Application of **Sport Floor**, elastomeric, modified, acrylic resins based paint, in water medium, with photostable pigmentation, to be applied in two coats over pavings, with a consumption of **Tender Item** 0,120 l/Sq.m., excluded practical operating loss.

(*) Le presenti informazioni, seppur ritenute attendibili, debbono essere considerate indicative, la società si riserva il diritto di variarli senza preavviso. L'uso delle presenti informazioni non implica alcuna responsabilità da parte nostra ivi compresa la violazione di eventuale licenza E' responsabilità degli utilizzatori verificare preventivamente l'idoneità del prodotto per l'impiego specifico. Per ulteriori chiarimenti o richieste specifiche riguardanti i prodotti si prega di contattare il responsabile del laboratorio tecnico.



Colorificio Atria



