



DRY CORNERIN DRY CORNEROUT

TECHNICAL DATA SHEET

revestech®



DRY CORNERIN



DRY CORNEROUT

Description

Waterproof reinforcement corners **DRY50** with thermoformed corner to cover indoor and outdoor 90° and 270° angles.

Reference	Description	Presentation
544010793	DRY CORNERIN	2 pcs. per bag
544010809	DRY CORNEROUT	2 pcs. per bag

CE MARKED MEMBRANE

1170/001-DdP-2013/07/01
EN 13956:2012



Features	Test Method	Unit	Tolerance	Value
Water tightness	EN 1928 Meth. B			PASS
Tensile strength	EN 12311-2 Meth. A	N/50 mm	MLV: L ≥ 395 MLV: T ≥ 130	L=395 T=130
Elongation	EN 12311-2 Meth. A	%	MLV: L ≥ 23 MLV: T ≥ 190	L=23 T=190
Overlap resistance	EN 12317-2	N/50 mm	MLV ≥ 110	110
Impact resistance	EN 12691	mm		PND
Static load resistance	EN 12730 Meth. B	Kg	MLV ≥ 20	20
Pliability at low temperature	EN 495-5	°C	MLV -40	-40
Reaction to fire	EN 13501-1	Euroclases		F
Length				see dimensions in picture
Weight	EN 1849-2	g/m ²	MDV: -5% e +10%	335
Thickness	EN 1849-2	mm	MDV: -5% e +10%	0,52
Visible defects	EN 1850-2			PASS
Straightness	EN 1848-2	mm	MLV: g ≤ 50	g=50
Flatness	EN 1848-2	mm	MLV: p ≤ 10	p=10
Resistance to diffusion water vapour	UNE-EN 1931:2001	m ² ·h·Pa/mg		9,75

MDV: Manufacturer's Declared Value. PND: No Performance Determined. MLV: Manufacturer's Limiting Value.



responsible
waterproofing

DRY CORNERIN DRY CORNEROUT

TECHNICAL DATA SHEET

revestech®

Further features	Test Method	Unit	Tolerance	Value
Dimensional stability	EN 1107-02	%	MLV: L ≤ -0.2 MLV: T ≤ 0	L= -0,2 T= 0
Water resistance of overlap cementitious adhesive C2	Water column	1 m/24 h		WATERTIGHT
Adhesion of adhesive cementitious C2 on the membrane sheet: TENSILE	Methodology CSTB	N/mm ²	± 10%	0,9
Adhesion of adhesive cementitious C2 on the membrane sheet: SHEAR STRESS	Methodology CSTB	N/mm ²	± 5%	1,28
Impact strenght with ceramic coating	Methodology CSTB	Number of shocks		4
Effects of chemicals	EN 1847	Values do not change after 28 days in saturated calcium hydroxide solution at 23 °C		

Storage

Store in original unopened packing, protect from moisture, in place properly ventilated at a maximum temperature of 30°C.
Protect from direct sunlight.